



AAACME RUBBER CO.

A Division of Fillipone Enterprises Inc.

2003 E. 5th Street, #1
Tempe, AZ 85288

Phone: 480-966-9311 Email: info@acmerubber.com

TECHNICAL SPECIFICATION SHEET

COMPOUND: 66903

POLYMER: SILICONE

PHYSICAL PROPERTIES TYPICAL

PROPERTY	TEST METHOD	TYPICAL VALUE
TENSILE STRENGTH (psi)	D412-16	850
ELONGATION (%)	D412-16	500
TEAR DIE B, ppi	D624-00(12)	105
SHORE A DUROMETER, pts	D2240-15e1	60±5
SPECIFIC GRAVITY, g/cm ³	D297-15	1.42

ALL TESTS PERFORMED FROM ASTM SLABS. TYPICAL VALUES ARE NOT TO BE CONSTRUED AS SPECIFICATIONS.

MATERIAL COMPLIANCE

FDA-MATERIAL COMPLIANCE

MEETS FDA REQUIREMENT RE: DRY FOOD CONTACT CFR 177.2600, ALL INGREDIENTS IN COMPOUND MEET REQUIREMENTS.

The data is based on testing, and to our knowledge, is accurate. Since applications, test methods, and procedures may vary, we recommend that users of our product perform their own tests to assure the suitability of these products for their application. We offer no product warranty, either expressed or implied, except any product proven defective will be replaced. Freedom from present or future infringement cannot be guaranteed, nor can the suitability for a specific application.