



AAAACME RUBBER CO.

A Division of Fillipone Enterprises Inc.

2003 E. 5th Street, #1

Tempe, AZ 85288

Phone: 480-966-9311 Email: info@acmerubber.com

75006 VITON "A"

Acme #75006 is a 55 durometer premium grade Viton compound. It has excellent resistance to aliphatic and aromatic hydrocarbons, petroleum oils, fuels, ozone and weather, lubricants, and animal or vegetable oils. It has a service temperature range of -10°F to 400°F.

Acme #75006 is not recommended for service in acids, chlorinated solvents, or hot water and steam.

Typical Physical Properties

PROPERTY	VALUE
Hardness (shore A)	55
Finish	Fabric Impression Finish
Tensile Strength (psi)	1000
Elongation at Break (%)	530%
Modulous at 300% Elongation (psi)	500
Tear Strength (ppi)	85
Specific Gravity	1.68
Compression Set (%) (22 Hours at 350°F)	56%

Viton™ is a trademark of The Chemours Company.

THE DATA PRESENTED IS BASED ON TESTING AND TO OUR KNOWLEDGE IS ACCURATE. SINCE APPLICATIONS, TEST METHODS AND PROCEDURES MAY VARY, WE RECOMMEND THAT USERS OF OUR PRODUCT PERFORM THEIR OWN TESTS TO ASSURE THE SUITABILITY OF THESE PRODUCTS FOR THEIR APPLICATION. WE OFFER NO PRODUCT WARRANTY, EITHER EXPRESSED OR IMPLIED, EXCEPT ANY PRODUCT PROVEN DEFECTIVE WILL BE REPLACED. FREEDOM FROM PRESENT OR FUTURE INFRINGEMENT CANNOT BE GUARANTEED, NOR CAN THE SUITABILITY FOR A SPECIFIC APPLICATION.

AAA-ACME Rubber Co.

A Division of Fillipone Enterprises Inc. • 2003 E. 5th Street, #1 • Tempe, AZ 85288

Phone: 480-966-9311 • Email: info@acmerubber.com