



AAAACME RUBBER CO.

A Division of Fillipone Enterprises Inc.

2003 E. 5th Street, #1

Tempe, AZ 85288

Phone: 480-966-9311 Email: info@acmerubber.com

SPECIFICATION SHEET

COMPOUND: 76009

DESCRIPTION: 60 DURO FLUOROELASTOMER COMPOUND IDEAL FOR EXTRUSION APPLICATIONS
(CONTAINS 66% FLUORINE, CHEMOURS VITON A)

PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUES
TENSILE PSI (Mpa):	1800 (12.1)
100% MODULUS, PSI (Mpa):	600 (4.1)
ULTIMATE ELONGATION, %:	240
SHORE A HARDNESS, Pts.:	60
SPECIFIC GRAVITY (H20=1):	1.92
COMPRESSION SET %: 22 HRS. @ 392°F	10
OPERATING TEMPERATURE:	-10 to 400°F

**CONFORMS TO ASTM D 2000 M2 HK 608 A1-10 B-38 C-12 EF-31 Z-1
Z1 HARDNESS SHORE "A" 65±5**

The data is based on testing, and to our knowledge, is accurate. Since applications, test methods, and procedures may vary, we recommend that users of our product perform their own tests to assure the suitability of these products for their application. We offer no product warranty, either expressed or implied, except any product proven defective will be replaced. Freedom from present or future infringement cannot be guaranteed, nor can the suitability for a specific application.

AAA-ACME Rubber Co.
A Division of FILLIPONE Enterprises Inc.
2003 East Fifth Street, Suite #1, Tempe, AZ 85288
Phone: 480-966-9311 | FAX: 480-966-2273
www.acmerubber.com | E-mail: info@acmerubber.com