



AAACME
RUBBER CO.

A Division of Fillipone Enterprises Inc.

2003 E. 5th Street, #1

Tempe, AZ 85288

Phone: 480-966-9311 Email: info@acmerubber.com

SPECIFICATION SHEET

Compound : #30079 CLOSED CELL NEOPRENE SPONGE

TYPICAL PHYSICAL PROPERTIES

COMPRESSION DEFLECTION (25%)	5-9
DENSITY P.C.F.	18±3
ASTM SPECIFICATION	D-1056-2C2
WATER ABSORPTION %	<5
COMPRESSION SET 22hrs. @ 23°C 50% DEF. 24 HOUR RECOVERY % (B3)	11
*WATER ABSORPTION, % (ASTM 1056-98)	<5
*FLUID RESISTANCE (ASTM D 1056-98) 7 Days @ 23 degrees C in Reference Fuel B Change in weight, %	+123
*COMPRESSION SET (ASTM D 1056-98, SUFFIX B2) 22 hrs. @ 23 degrees C, 50% deflection 24 hr. recovery, %	11
HEAT RESISTANCE: COMPRESSION DEFLECTION (ASTM D 1056-98, SUFFIX A1) Oven-aged 22 hrs. @ 100 degrees C Change from original C/D value, %	0
*HEAT RESISTANCE: COMPRESSION DEFLECTION (ASTM D 1056-98) Oven-aged 7 days @ 70 degrees C Change from original C/D value, %	-1
FLAMMABILITY OF INTERIOR MATERIALS FMVSS 302 (SUFFIX Z2)	PASS
STANDARD COLORS	BLACK

The data is based on testing, and to our knowledge, is accurate. Since applications, test methods, and procedures may vary, we recommend that users of our product perform their own tests to assure the suitability of these products for their application. We offer no product warranty, either expressed or implied, except any product proven defective will be replaced. Freedom from present or future infringement cannot be guaranteed, nor can suitability for a specific application.