



AAA-ACME RUBBER

A Division of FILLIPONE Enterprises Inc.

2003 E. 5th Street, #1
Tempe, AZ 85288
Phone: 480-966-9311 | Email: info@acmerubber.com

SPECIFICATION SHEET

MATERIAL IDENTIFICATION

ACME COMPOUND:	#66969
POLYMER:	SILICONE PLATINUM CURED
COLOR:	TRANSLUCENT

PHYSICAL PROPERTIES (TYPICAL)

TEMPERATURE RANGE:	-65°F to +450°F
HARDNESS, SHORE A:	60 ± 5 DURO
TENSILE STRENGTH:	1300 PSI
ELONGATION:	450%
TEAR STRENGTH:	180 PPI

FDA NOTE:

MATERIAL MEETS FDA REQUIREMENT RE: DRY FOOD CONTACT CFR 177.2600, ALL INGREDIENTS IN COMPOUND MEET REQUIREMENTS.

DISCLAIMER:

THE DATA PRESENTED IS BASED ON TESTING AND TO OUR KNOWLEDGE IS ACCURATE. SINCE APPLICATIONS, TEST METHODS AND PROCEDURES MAY VARY, WE RECOMMEND THAT USERS OF OUR PRODUCT PERFORM THEIR OWN TESTS TO ASSURE THE SUITABILITY OF THESE PRODUCTS FOR THEIR APPLICATION. WE OFFER NO PRODUCT WARRANTY, EITHER EXPRESSED OR IMPLIED, EXCEPT ANY PRODUCT PROVEN DEFECTIVE WILL BE REPLACED. FREEDOM FROM PRESENT OR FUTURE INFRINGEMENT CANNOT BE GUARANTEED, NOR CAN THE SUITABILITY FOR A SPECIFIC APPLICATION.